



ISO-9001 Registered Quality System.

**Sales, Service & Distribution Center**

Newark, NJ 07105

Phone: 973-589-9150 Fax: 973-589-4432

**Manufacturing, Sales, Service & Distribution Center**

Toledo, OH 43605

Phone: 419-691-2491 Fax: 419-693-3806

**Sales and Tech Service Support**

Phone: 1-800-733-4755

**PRODUCT DATA****LUBRIPLATE No.'s 130-A & 130-AA****DESCRIPTION**

LUBRIPLATE No's. 130-A & 130-AA are designed for those applications where a grease-type lubricant possessing extremely good water repellency and superior lubrication characteristics are desired.

**APPLICATIONS**

These products are recommended for:

- ⇒ Plain bearings
- ⇒ Cams
- ⇒ Guides
- ⇒ Open gears
- ⇒ Slides and chassis lubrication
- ⇒ Where temperatures do not exceed 170°F

**STORAGE RECOMMENDATIONS**

- ⇒ Products should be stored between 40°F-120°F
- ⇒ Products should be stored in a dry covered environment
- ⇒ Products should not be stored in warm, direct sunlight
- ⇒ Improper storage conditions can significantly alter the shelf life of the product. Such conditions would include temperature, moisture, open containers, etc.

**Typical Test Data**

PROPERTY	TEST METHOD	TYPICAL RESULTS*	
		No. 130-A	No. 130-AA
Type of Base		Calcium	Calcium
Worked Penetration	ASTM D-217	220/265	310/340
NLGI No.		2 / 3	1
ASTM Melting Point	ASTM D-87	200°F/93°C	190°F/88°C
<b>Mineral Oil Viscosity:</b>			
SUS @ 100°F	ASTM D-2161	750	750
cSt @ 40°C	ASTM D-445	135	135
Color	Visual	Beige	Beige
Character		Smooth	Smooth

**PACKAGING AVAILABLE**

Carton, 12/16 oz. Plastic Tubs  
 Carton, 4/6 lb. Plastic Tubs  
 35 lb. Pail  
 120 lb. Quarter Size Drum  
 420 lb. Full Size Drum  
 Carton, 36/1¼ oz. Tubes (1X6)  
 Carton, 36/10 oz. Plastic Tubes

**No. 130-A**

L0043-004  
 L0043-005  
 L0043-035  
 \*\*\*  
 L0043-040  
 \*\*\*  
 \*\*\*

**No. 130-AA**

L0044-004  
 L0044-005  
 L0044-035  
 L0044-039  
 L0044-040  
 L0044-086  
 L0044-092

