

CORROSION INHIBITING COMPOUNDS

COR-BAN[®] 23 ENHANCED DYE

ENHANCED DYE Product description: CORROSION INHIBITING

COMPOUND

FEATURES:

- A long lasting, high penetration, and water displacing corrosion inhibiting compound
- Has a stronger dye than regular Cor-Ban[®] 23
- May be used in the place of Airbus CML 15-006

KEY BENEFITS:

- Free of chromates
- Free from heavy metals
- Low toxicity
- Offers inhibition and a thin film
- Water displacing
- Very low dry film weight <0.3 mil (8 microns) required to surpass specification</p>
- Non-cracking and non-flaking to -65°F (-54°C)
- Non-sagging, fast drying, non-tacky, and detectable film

Rev: 29125E 08-16-2023







Cor-Ban®

CORROSION INHIBITING COMPOUNDS

COR-BAN[®] 23 ENHANCED DYE

Product description: CORROSION INHIBITING

KEY BENEFITS:

- Solvent removable
- Strong dye allows for easy visual detection
- > 3000 Hours Salt Spray

SPECS:

- Airbus AIMS 09-08-001 Type I Grade 3
- Bombardier BAMS 565-006 Type V
- Boeing BMS 3-23J Type II Class 2 Grade A & B (QPL)
- Boeing BMS 3-35
- Fed-Ex E.O. 9-5100-7-5001

APPLICATIONS:

- ✓ Apply by conventional airless, air-operated spray equipment, or by aerosol
- ✓ Use on high profile aircraft substrates, upper edge floor beams, wheel wells, pressure deck, and center wing sections
- The Cor-Ban® 23 Enhanced Dye aerosol can be used in conjunction with the Formit® extensions to provide targeted spray to areas that may be difficult to reach but need to be coated. Please refer to the Formit® technical data sheet for more information.
- ✓ All properties represented were achieved with a dry film thickness of range 0.3 0.5 mils (7-12 microns)
- ✓ The wet film will self level to achieve the desired dry film thickness when applied to an inclined surface
- ✓ One aerosol can covers approximately 160 ft² (14.9 m²) and one gallon (3.8L) of bulk material covers approximately 2290 ft² (56.2 m²/liter).





Cor-Ban®

CORROSION INHIBITING COMPOUNDS

COR-BAN[®] 23 ENHANCED DYE



Product description: CORROSION INHIBITING COMPOUND

PHYSICAL PROPERTIES:

- **Color:** Transparent Reddish-Pink
- Drying Time: <1 hour</p>
- Exfoliation: Pass at -65°F (-54°C)
- **Flash Point:** 114°F (45°C)
- Low Temp Flaking: Pass
- Non-Volatiles: 42%
- Operating Temperature: -65°F (-54°C) to 350°F (177°C)
- Penetration: >4 inches per hours per BMS 3-35
- Salt Spray Protection: >3000 hours on aluminum
- Specific Gravity: 0.88
- Viscosity: 35-40 cps.
- Water Displacement: 0% Rust

AVAILABLE PACK SIZES:

- Case of 12 of 16 fl oz (473 ml) Aerosols-011321
- 5 Gallon (18.9L) Pail-011209
- Special Packaging Upon Request

For more information contact us : zipchem@addevmaterials.com

