

PRODUCT DATA SHEET

PHYSICAL CHARACTERISTICS

ColorGreenish BrownVolume Solids>92%AppearanceClearFilm Thickness0.0004"OdorFresh ScentpHNASpecific Gravity @ 15.6°C0.895Vapor Pressure @ 38°C>1mm Hg.

Viscosity, cSt @ 40°C 33.2 Solubility in Water Slightly Emulsifiable

cSt @ 100°C 7.0 Boiling Point >200°C Flash Point c.o.c. 143°C Weight per Gallon 7.46 lbs.

Coverage Approx. 3,3000 sq ft / gal

PERFORMANCE PROPERTIES

Electrical:

Lubrication:

Corrosion Protection: Salt Spry, hrs. >336* ASTM B117

(Film Thickness) 0.19 mils

Humidity Cabinet, hrs. >1320 ASTM D1748
Dielectric Strength >39,000V (typ.) ASTM D877
Anti-Wear 0.249 mm** ASTM D4172

COMPATIBILITY WITH MATERIALS

<u>Rubber:</u> No visible effect on Nitrile / Buna-N, Viton® or Neoprene products. Slight swelling and/or softening of butyl rubber items.

<u>Adhesives and Sealants:</u> Usually no effect but some adhesives may soften and sealants with silicone may experience slight swelling. Recommend a small test sample prior to widespread application.

<u>Painted Surfaces:</u> Paints typically used on aircraft, automobiles and machinery are unaffected by CorrosionX. Polishes and some wax coatings may soften by the application of *any* hydrocarbon product.

<u>Plastics / Composites:</u> CorrosionX is compatible with most commonly-encountered plastics such as: acrylic, polyester, nylon, vinyl, Delrin^{®*}, PTFE, Formica^{®**}, polyethylene and polypropylene. Should there be any question when other types of plastics are involved, it is suggested a small sample be tested.

Fabrics: CorrosionX will be absorbed into the fibers of most fabrics, thereby creating slight staining. The stain is not permanent and may be removed with naphtha or mineral spirits.

Storage: Bulk: Store at room temperatures (50°F or more). Aerosols not more than 120°F.

Shelf Life: Bulk: Indefinite (as long as container remains capped). Aerosols: 3 years

^{**}Polished 1020 carbon steel panel. 0 - <1% surface rust

^{**}Note: The smaller the number, the better the performance. A standard lubricating oil of the same viscosity would yield a value of 1.0 - 1.2 mm.

^{*}Registered trademark of E.I. Dupont de Nemours

^{**} Registered trademark of Formica Corp