

# Technical Data Sheet

## Skydrol® 5 Hydraulic Fluid

### Applications

- Aviation hydraulic fluid

### Product Description

Introduced in 1996, Skydrol 5 was the first Type V fluid qualified under the Boeing BMS 3-11 specification. Skydrol 5 offers higher temperature capability than Type IV fluids, the lowest density, and better paint compatibility. Skydrol 5 does not have universal air frame manufacturer approval, so consult Eastman's Skydrol Technical Service (800-260-4150) for specific approval and application information.

### Typical Properties

Property	Test Method	Typical Value, Units
<b>General</b>		
Acid Number (mg KOH/g)		0.10 Maximum
Appearance		Clear, oily liquid
Autoignition Temperature	ASTM D 2155	399 °C (750 °F ) Minimum
Color		Purple, essentially equivalent to intensity and hue standard
Elemental Content		
Calcium		10 ppm, Maximum
Chlorine		50 ppm, Maximum
Potassium		30 ppm, Maximum
Sodium		10 ppm, Maximum
Sulfur		1185-1540 ppm
Flash Point		
COC		154 °C (310 °F ) Minimum
Moisture		0.20 % Maximum
Particle Contamination <sup>a</sup>		
15-25 micron size		5,700 Maximum
25-50 micron size		1,012 Maximum
50-100 micron size		180 Maximum
5-15 micron size		32,000 Maximum
Over 100 micron size		32 Maximum
Pour Point		-62 °C (-80 °F ) Maximum
Specific Gravity		
@ 25°C/25°C		0.970-0.980
Viscosity		
@ 38°C (100°F)		9.00-9.84 cSt
@ -54°C (-65°F)		2600 cSt Maximum
@ 99°C (210°F)		3.01-3.41 cSt

<sup>a</sup>NAS 1638 particle counts per AS4059F

*and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

2/28/2018 11:35:39 AM

© 2023 Eastman Chemical Company or its subsidiaries. All rights reserved. As used herein, ® denotes registered trademark status in the U.S. only.